## **Cipoxy FC 500 TE**

Solvent free texture floor coating

■ Cipoxy FC 500 TE is used as a topcoat

in conjunction with Cipoxy range of floor

■ It is recommended in automobile, pharma,

food, brewery and light engineering

It is food grade epoxy floor coating.

## Description

A two component epoxy based pigmented top coat, cured with modified cyclo-aliphatic curing agent, Cipoxy FC 500 TE is recommended as a solvent free textured floor coating. It has excellent adhesion over primed and screeded surfaces. It is available in RAL colours

#### Uses

## **Key feature**

- Excellent adhesion
  - Solvent free
  - levelling Excellent flow and characteristics
- High gloss
- Excellent toughness
- Texture finish

**Properties** 

toppings.

industries.

Туре	: Epoxy cyclo-aliphatic amine	Mixing ratio	:	Pre-weighed packs
Finish	:High gloss	Colour	:	Desired shade
Pot life @ 27ºC ASTM D 2471	: ≥ 40 minutes	Volume solids ASTM D 2697	:	94%
Drying time ASTM D 1640		Recommended DFT ASTM D 7091	:	500 microns
Surface dry	: ≥ 2 hrs			
Tack free dry	: ≥ 7 hrs			
Hard dry	: ≥ 24 hrs			
Recommended thinner	:PUT 502 (Clean up)	Shelf life	:	12 months in the unopened container

## **Performance data**

The mandatory performan FeFRA and EFNARC guid system		Other mechanical properties		
Pull of adhesion test ASTM D 7234-2022	: ≥ 2 MPa for M20 grade concrete or Concrete failure	Tensile strength ASTM D 638	: 15 MPa	
Impact resistance ASTM D 2794 - 1993 Falling weight : 1 kg	: 8.83 N.m	Shore D ASTM D 2240	: 50 - 55	
Abrasion resistance ASTM D 4060-2019 CS 17, 1 kg 1000 cycles	: Maximum 38 mg loss	Pendulum test Slip resistance BS 8204	: 45 - 50 (low risk of slip)	

Note: The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions

Certified

**TYPE 3 EFNARC GUIDELINE** 



## Cipoxy FC 500 TE

Solvent free texture floor coating



## **APPLICATION INSTRUCTIONS**

#### **Surface preparation**

The long-term durability of the applied Cipoxy FC 500 TE is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application. Ensure that the residual moisture level in the concrete is below 5%. All substrates should be sound and free from contamination such as mortar and paint splashes, curing compound residue, oil, or grease. Excessive laitance should be removed by light mechanical scrabbling, grinding or grit blasting. Oil and grease contamination must be completely removed by grinding down to sound, clean concrete. Alternatively, blasting techniques can be used to provide the required substrate.

#### Priming

Prepared substrates to be treated with Cipoxy FC 500 TE, should be primed with CIPOXY 17/18 primer should be mixed in the proportions supplied by adding the entire contents of hardener can to the base can. Once mixed the CIPOXY 17/18 should be immediately applied in a thin, continuous film using stiff brushes or rollers. Over application and puddles should be avoided. Porous floors may require two coats of CIPOXY 17/18 primer. CIPOXY 17/18 primer should be allowed to become tack free prior to application. Primer coverage will depend on the texture and porosity of the substrate and also the application thickness.

## **Mixing & Application**

Cipoxy FC 500 TE is supplied in pre-weighed packs ready to use on site. Solvent or thinners should not be added. Mix all the pack material quantity in a bowl and stir for 2-3 minutes using slow speed mixer. The material is poured on to the primed surface and spread to the desired thickness and then use a special kind of epoxy roller / sponge or nylon roller

#### **Packaging and coverage**

Cipoxy FC 500 TE	:	Pre-weighed Clear set of 17.99 kgs	:	1 set covers 23 sqm @ 500 microns
Cipoxy 17/Cipoxy 18	:	Resin and Hardener available in 20 litre packing	:	1 litre covers 5 sqm @ 200 microns

## **Storage and handling**

The product should be stored in accordance with national regulations. It should be kept in a cool, well ventilated area, away from heat, direct sunlight, sparks and children. Handle with care. Ideal temperature for storage of the material is 25°C to 30°C, in a covered shed.

Do's	Don't		
Clean regularly	Drag any sharp and heavy object		
Remove aggressive chemical spillage immediately	Expose to fire or welding spark		
Maintain wheel for proper rolling, should not getdragged.	Expose to very high temperature than recommended by Manufacturer		
Handle heavy material gently and cautiously			
Clean any oil or any liquid which may cause accident	Drop down and heavy material on the floor		
during people's movement	Expose to highly corrosive chemicals		

#### Limitations

It is not compatible for application over asphalt, unmodified sand-cement screeds or PVC tiles and sheets. CIPOXY FC 500 TE coating laid floor will be scratched due to nails or sharp objects protruding from machinery, packings, or trolleys moving on the floor. Presence of sand will also cause abrasion.

The product is not advised to be applied below  $15^{\circ}$ C as the flow reduces. While applying the product above  $35^{\circ}$ C, here can be a problem of low pot life etc., and it will be difficult to apply the material. Cured product is not suitable for exposure to sub-zero temperatures and above 650C. When there is not enough material in a given area, roller marks caused due to spiked rolling may not close which will result in an undesirable finish. The product is not suitable for areas exposed to direct sunlight

# Cipoxy FC 500 TE

Solvent free texture floor coating



## Health and safety precautions

Please refer to MSDS. Observe reasonable care and employ ordinary hygienic principles such as washing the hands with soap and water before eating or smoking. It is recommended to wear gloves, goggles and nose masks while application. Incase of splashes on the skin, dampen the cloth with thinner PUT 503 and wipe the hands with the cloth. Wash then with soap.

#### Other Products Categories available Dr.Cipy brings you the widest range of Flooring Systems



Pidilite Pidilite Industries Ltd. T-127, MIDC, Bhosari, Pune - 411 026

Tel. +91-20-66316400 Email : drcipy@pidilite.com **DISCLAIMER:** All information contained in this data sheet is given to the best of our knowledge but no warranty is made with respect thereto. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest edition. Description and advice regarding Cipy's products are based on long term field and laboratory tests carried out by us. No condition of warranty is given covering the results from the use of materials in the circumstances of any particular application, because the storage, handling and application of the materials are beyond our control.