

Spartikote CG

Polyaspartic UV resistance fast curing clear floor coating



Description

Spartikote CG is the new generation, two component, UV stable floor coating. Spartikote CG has exceptional abrasion resistance, superior adhesion and is rapid curing top coat over all resin flooring and aggregates broadcast epoxy systems.

Uses

- Fast curing top coat where UV resistance is required
- Fast setting excellent for maintenance works
- High build roller applied coating on all resin flooring

Key features

- UV resistance and clear coat
- Fast cure within 4 hours
- Excellent gloss
- Excellent abrasion and impact resistance
- Excellent hot tyre pick up resistance
- Can be applied in severe winter
- No blushing at low temperature

Properties

| | | | |
|--------------------------------|-----------------------------------|------------------------------|---------------------------------------|
| Type | : Polyaspartic aliphatic polyurea | Mixing ratio | : Pre-weighed kit |
| Finish | : Smooth and glossy | Volume Solids ASTM D 2697 | : 86% |
| Pot life @ 25°C ASTM D 2471 | : 30 minutes | Recommended DFT | : 270 - 280 microns |
| Drying time ASTM D 1640 | | Application | : By roller |
| Surface dry | : 30 minutes | Shelf life | : 12 months in the unopened container |
| Tack free dry | : 2 ½ to 3 hrs | | |
| Recommended thinner | : PUT 502 (Clean up) | | |

Performance data

The mandatory performance parameters as per FeFRA and EFNARC guidelines for resin flooring system

| | |
|--|--|
| Pull of adhesion test ASTM D 4541 | : ≥ 2 MPa for M20 grade concrete or Concrete failure |
| Abrasion resistance ASTM D 4060 | : Max 42 mg loss (in 1000 cycles) |
| Impact resistance IS 101 (Part 5 / Sec 3) | : Pass (1.8 kg - 60 cm) |
| Slip resistance BS 8204 | : 69 PTV - low risk of slip |

Other mechanical properties

| | |
|---|-------------------|
| Tensile strength ASTM D 638 | : ≥ 22 MPa |
| Elongation ASTM D 638 | : 16% |
| Scratch resistance IS 101, Part 5, Sec 2 | : 4 kg acceptable |
| Shore D Hardness ASTM D 2240 | : 75 |

Note : The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions

Spartikote CG

Polyaspartic UV resistance fast curing clear floor coating

APPLICATION INSTRUCTION

ON EXISTING RESIN TOPPING

Prepare the surface of the existing coating using mechanical grinding equipment. Remove dust and contamination from the prepared surface using vacuum extraction equipment. No primer is required for application of Spartikote CG on existing epoxy, PU, EPU, PU Concrete and Polyaspartic.

MIXING AND APPLICATION

Spartikote CG is supplied in pre-weighed pack. Solvent or thinners should not be added. A forced action mixer with a paddle fitted into a heavy duty, slow speed electric hand drill is recommended for mixing. The material is poured onto the prepared substrate and spread to the required thickness with a roller and allow to cure for minimum 4 hours.

Packaging & Coverage

Spartikote CG : Pre weighed kit of 3 kgs : 1 set covers 9 sqm @ 270 to 280 microns DFT

Storage and handling :

The product should be stored in accordance with national regulations. It should be kept in a cool, well ventilated area, away from heat, direct sunlight, sparks and children. It contains inflammable solvents. Handle with care. Mix resin and hardener as per the ratio. Use the mix solution within the pot life time. Ideal temperature for storage of the material is 25°C to 30°C, in a covered shed.

Health and safety precautions

Please refer to MSDS. Observe reasonable care and employ ordinary hygienic principles such as washing the hands with soap and water before eating or smoking. It is recommended to wear gloves, goggles and nose masks while application. In case of splashes on the skin, dampen the cloth with thinner PUT 503 and wipe the hands with the cloth. Wash then with soap and water. Dried film is non toxic. In case of contact with eyes, rinse with plenty of water and seek medical advice. In case of continuous exposure to vapour, the applicator should be immediately moved to get fresh air. The disposal of excess or waste material should be carried out in accordance with the local legislations.

Do's

Clean regularly
Remove aggressive chemical spillage immediately
Maintain wheel for proper rolling, should not get dragged.
Nylon / teflon wheel trolleys are recommended
Immediately clean spillage of any oil or fatty liquid which may cause accident during people's movement

Don't

Drag any sharp and heavy object. Movement of metal wheel trolley
Expose to fire or welding spark
Expose to very high temperature than recommended by Manufacturer
Drop down any heavy material on the floor
Expose to highly corrosive chemicals

Limitations


It is not compatible for application over asphalt, unmodified sand-cement screeds or PVC tiles and sheets. Spartikote CG laid floor will be scratched due to nails or sharp objects protruding from machinery, packings, or trolleys moving on the floor. Presence of sand will also cause abrasion. The product is not advised to be applied below 15°C as the flow reduces. While applying the product above 35 °C, there can be a problem of low pot life etc., and it will be difficult to apply the material. Cured product is not suitable for exposure to sub-zero temperatures and above 65°C. When there is not enough material in a given area, roller marks caused due to spiked rolling may not close which will result in an undesirable finish.

Spartikote CG

Polyaspartic UV resistance fast curing clear floor coating



Other Products Categories available
Dr.Cipy brings you the widest range of Flooring Systems



Pidilite Industries Ltd.

T-127, MIDC, Bhosari, Pune - 411 026

Tel. +91-20-66316400

Email : drcipy@pidilite.com

DISCLAIMER: All information contained in this data sheet is given to the best of our knowledge but no warranty is made with respect thereto. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest edition. Description and advice regarding Cipy's products are based on long term field and laboratory tests carried out by us. No condition of warranty is given covering the results from the use of materials in the circumstances of any particular application, because the storage, handling and application of the materials are beyond our control.