

Spartikote CG

Polyaspartic UV resistance fast curing clear floor coating

TYPE 3 EFNARC GUIDELINE

HIGH BUILD FLOOR COATING

Description

Spartikote CG is the new generation, two component, UV stable floor coating. Spartikote CG has exceptional abrasion resistance, superior adhesion and is rapid curing top coat over all resin flooring and aggregates broadcast epoxy systems.

Uses

- Fast curing top coat where UV resistance is required
- Fast setting excellent for maintenance works
- Stand alone product as high build roller applied coating on all resin flooring

Key features

- UV resistance and clear coat
- Fast cure within 4 hours
- Excellent gloss
- Excellent abrasion and impact resistance
- Excellent hot tyre pick up resistance
- Can be applied in severe winter
- No blushing at low temperature

Properties

Type	: Polyaspartic aliphatic polyurea	Mixing ratio	: Pre-weighed kit
Finish	: Smooth and glossy	Volume Solids ASTM D 2697	: 82%
Pot life @ 25°C ASTM D 2471	: 30 minutes	Recommended DFT	: 270 - 280 microns
Drying time ASTM D 1640		Application	: By roller
Surface dry	: 30 minutes	Shelf life	: 12 months in the unopened container
Tack free dry	: 2 ½ to 3 hrs		
Recommended thinner	: PUT 502 (Clean up)		

Note : The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions

Spartikote CG

Polyaspartic UV resistance fast curing clear floor coating

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

CONCRETE SUBSTRATE PREPARATION :

The long-term durability of the applied Spartikote CG coating is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application. Ensure that the residual moisture level in the concrete is above 5%. All substrates should be sound and free from contamination such as mortar and paint splashes, curing compound residue, oil, or grease. Excessive laitance should be removed by light mechanical scrubbing, grinding or grit blasting. Oil and grease contamination must be completely removed by grinding down to sound, clean concrete. Alternatively, blasting techniques can be used to provide the required substrate.

PRIMING

Prepared substrates to be treated with Spartikote CG coating, should be primed with Cipoxy 17/18. Primer should be mixed in the proportions supplied by adding the entire contents of hardener can to the base can. Once mixed the Cipoxy 17/18 should be immediately applied in a thin, continuous film using stiff brushes or rollers. Over application and puddles should be avoided. Porous floors may require two coats of primer. It should be allowed to become tack free prior to application. Primer coverage will depend on the texture and porosity of the substrate and also the application thickness.

ON EXISTING RESIN TOPPING

Prepare the surface of the existing coating using mechanical grinding equipment. Remove dust and contamination from the prepared surface using vacuum extraction equipment. No primer is required for application of Spartikote CG on existing epoxy, PU, EPU and PU concrete.

MIXING AND APPLICATION

Spartikote CG is supplied in pre-weighed pack. Solvent or thinners should not be added. A forced action mixer with a paddle fitted into a heavy duty, slow speed electric hand drill is recommended for mixing. The material is poured onto the prepared substrate and spread to the required thickness with a roller and allow to cure for minimum 4 hours.

Packaging & Coverage

Spartikote CG : Pre weighed kit of 3 kgs : 1 set covers 9 sqm @ 270 to 280 microns DFT

Storage and handling :

The product should be stored in accordance with national regulations. It should be kept in a cool, well ventilated area, away from heat, direct sunlight, sparks and children. It contains inflammable solvents. Handle with care. Mix resin and hardener as per the ratio. Use the mix solution within the pot life time. Ideal temperature for storage of the material is 25°C to 30°C, in a covered shed.

Health and safety precautions

Please refer to MSDS. Observe reasonable care and employ ordinary hygienic principles such as washing the hands with soap and water before eating or smoking. It is recommended to wear gloves, goggles and nose masks while application. In case of splashes on the skin, dampen the cloth with thinner PUT 503 and wipe the hands with the cloth. Wash then with soap and water. Dried film is non toxic. In case of contact with eyes, rinse with plenty of water and seek medical advice. In case of continuous exposure to vapour, the applicator should be immediately moved to get fresh air. The disposal of excess or waste material should be carried out in accordance with the local legislations.

Spartikote CG

Polyaspartic UV resistance fast curing clear floor coating

Do's

- Clean regularly
- Remove aggressive chemical spillage immediately
- Maintain wheel for proper rolling, should not get dragged. Nylon / teflon wheel trolleys are recommended
- Immediately clean spillage of any oil or fatty liquid which may cause accident during people's movement

Don't

- Drag any sharp and heavy object. Movement of metal wheel trolley
- Expose to fire or welding spark
- Expose to very high temperature than recommended by Manufacturer
- Drop down any heavy material on the floor
- Expose to highly corrosive chemicals

Limitations

It is not compatible for application over asphalt, unmodified sand-cement screeds or PVC tiles and sheets. Spartikote CG laid floor will be scratched due to nails or sharp objects protruding from machinery, packings, or trolleys moving on the floor. Presence of sand will also cause abrasion. The product is not advised to be applied below 15°C as the flow reduces. While applying the product above 35 °C, there can be a problem of low pot life etc., and it will be difficult to apply the material. Cured product is not suitable for exposure to sub-zero temperatures and above 65°C. When there is not enough material in a given area, roller marks caused due to spiked rolling may not close which will result in an undesirable finish.

Other Products Categories available

Dr.Cipy brings you the widest range of Flooring Systems

